

ELASTOPHENE®

HS SANDED

ELASTOPHENE®
HS SANDED
PRODUCT # 00564

DESCRIPTION & FEATURES

ELASTOPHENE HS Sanded (high strength) is an SBS-modified bitumen base ply for use in approved multi-ply membrane and flashing assemblies. ELASTOPHENE HS Sanded is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a tough, dimensionally stable composite polyester/glass fiber reinforcement. The topside and underside are surfaced with fine mineral aggregate to facilitate cold adhesive application.

STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOPHENE HS Sanded.

APPLICATION

Prior to installation, unroll ELASTOPHENE HS Sanded onto the roof surface and allow to relax. Place ELASTOPHENE HS Sanded in desired position and back roll the product. Apply approved cold adhesive following manufacturer specifications. ELASTOPHENE HS Sanded is then rolled into the cold adhesive and subsequently rolled with a weighted roller. Subsequent approved inter-ply or cap ply membranes are applied to ELASTOPHENE HS Sanded via cold adhesive. Refer to the SOPREMA SBS Roofing Guide for additional application guidelines.



APPLICATION



COLD ADHESIVE

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft ²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
D6162 Type 3, Grade S	33 (10.0 m)	39 (1.0 m)	97.5 (9.1 m ²)	118 (3.0 mm)	73 (33.2 kg)	30 (2,240 lbs/ 1,016 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations.



SOPREMA®

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Composite polyester/glass fiber
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Sanded
Back surfacing	Sanded
Selvage width, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	118 (3.0)	ASTM D5147
Net mass per unit area, lb/100ft ² (g/m ²)	68 (3321)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	405 (70.8)	375 (65.6)	ASTM D5147
Elongation at maximum load @ 0°F (-18°C), %	7	8	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	290 (50.8)	285 (49.9)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	10	10	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	15	20	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	540 (2402)	550 (2402)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.5	< 0.5	ASTM D5147
Compound stability, °F (°C)	240 (116)	240 (116)	ASTM D5147

* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS

FLORIDA BUILDING CODE

MIAMI-DADE COUNTY
APPROVED