

VERSIFLEECE® TPO MEMBRANES



Overview

VersiFleece TPO membranes with Octaguard XT™ are manufactured using a hot-melt extrusion process for complete scrim encapsulation. Once the VersiWeld® TPO is reinforced and enhanced with fleece, the total sheet thicknesses available are 100, 115 and 135 mils creating a very tough, durable and versatile sheet that is ideal for re-roofing or new construction projects. VersiFleece TPO sheets are chlorine free and plasticizer free with excellent chemical resistance to acids, bases, restaurant oils and greases.

All VersiFleece TPO membranes utilize OctaGuard XT weathering package technology to withstand extreme durability testing intended to simulate exposure to severe climates. VersiFleece TPO's advanced polymerization technology combines the flexibility of ethylene-propylene (EP) rubber with the heat weldability of polypropylene.

VersiFleece TPO membranes are intended to be used with adhered or mechanically fastened roofing systems. VersiFleece TPO is ideally suited for roof garden and solar panel applications and projects demanding superior wind uplift resistance due to its added toughness and durability. VersiFleece TPO is also a great solution for buildings requiring low noise and odors during roofing application.

Features and Benefits

- Choice of white, gray or tan membranes that are UL Class A rated
- Superior wind uplift performance and ratings (up to an FM 1-945) due to a mechanical bond between fleece and adhesive
- 75% fewer seams than Modified Bitumen
- Wide window of weldability
- Fleece reinforcement adds toughness, durability and enhanced puncture resistance
 - 115-mil membrane delivers 33% greater puncture resistance and 33% greater breaking strength than 60-mil TPO
 - Greater puncture resistance than Modified Bitumen
- Excellent hail damage resistance
 - Passes FM's severe hail test
 - Passes UL-2218 Class 4 rating
 - Passes National Bureau of Standards – 23 Ice Ball test up to 3"-diameter hail with the membrane cooled to 32°F
- APEEL™ Protective Film application guards the TPO membrane's surface from scuffs and dirt accumulation during installation, improving the roof system's appearance and long-term performance
- APEEL Protective Film can be left in place for up to 90 days without degrading due to its excellent heat- and UV-resistance



Labor Saving Features and Benefits: Optional APEEL Protective Film

Versico's VersiFleece TPO reinforced membrane is available with an optional APEEL Protective Film, saving time and labor by eliminating the need for roof cleaning upon project completion. Versico's innovative APEEL Protective Film can be left in place for up to 90 days without affecting the integrity of the film, guarding the TPO membrane's surface from scuffs and dirt accumulation during installation. Durable and easy to remove, APEEL Protective Film improves aesthetics and long-term reflectivity and is ideal for re-roofing, re-cover, and new construction projects.



Installation

Adhered Roofing System

Insulation is mechanically attached or adhered. Spray-apply or extrude Flexible DASH Adhesive to the substrate and allow foam to "string/body" approximately 1–2 minutes prior to setting VersiFleece TPO into the Flexible DASH adhesive. Roll VersiFleece TPO membrane with a 30"-wide 150-pound weighted roller to ensure full embedment. Splices are hot-air welded. End laps are butted and sealed with reinforced membrane or a head sheet may be utilized.

REVIEW CURRENT VERSICO SPECIFICATIONS AND DETAILS FOR SPECIFIC INSTALLATION REQUIREMENTS.

Precautions

1. Use proper stacking procedures to ensure sufficient stability.
2. Exercise caution when walking on wet membrane.
3. UV-resistant sunglasses are required for VersiFleece TPO membranes.
4. White surfaces reflect heat and may become slippery due to frost and ice accumulation.
5. Care must be exercised when working close to a roof edge when the surrounding area is snow covered.
6. VersiFleece TPO membrane rolls must be tarp and elevated to keep dry prior to installation. If the fleece gets wet, use a wet vac system to help remove moisture from the fleece. **DO NOT INSTALL MEMBRANE IF FLEECE IS WET.**
7. VersiFleece TPO membrane exposed to the weather must be prepared with Weathered Membrane Cleaner prior to hot-air welding.

Supplemental Approvals, Statements and Characteristics:

1. VersiFleece TPO meets or exceeds the requirements of ASTM D6878 Standard Specification for Thermoplastic Polyolefin-Based Sheet Roofing
2. Radiative Properties for ENERGY STAR, Cool Roof Rating Council (CRRC) and LEED.
3. VersiFleece TPO membranes conform to requirements of the US E.P.A. Toxic Leachate Test (40 CFR part 136) performed by an independent analytical laboratory.
4. VersiFleece TPO was tested for dynamic puncture resistance per ASTM D5635-04 using the most recently modified impact head. 45-mil was watertight after an impact energy of 12.5 J (9.2 ft-lbf) and 60-mil was watertight after 22.5 J (16.6 ft-lbf). 80-mil was watertight after an impact energy of 30.0 J (22.1 ft-lbf).
5. NSF-P151 Certification for rainwater catchment system components.
 - Plant 91/White Only

LEED® INFORMATION

Pre-consumer Recycled Content	10%
Post-consumer Recycled Content	0%
Manufacturing Location	Tooele, UT, Senatobia, MS
Solar Reflectance Index	White: 99 Gray: 53 Tan: 86

RADIATIVE PROPERTIES FOR ENERGY STAR®, COOL ROOF RATING COUNCIL (CRRC) AND LEED

Physical Property	Test Method	White	Gray	Tan
ENERGY STAR – Initial solar reflectance	Solar Spectrum Reflectometer	0.79	N/A	0.71
ENERGY STAR – Solar reflectance after 3 years	Solar Spectrum Reflectometer (uncleaned)	0.70	N/A	0.64
CRRC – Initial solar reflectance	ASTM C1549	0.79	0.46	0.71
CRRC – Solar reflectance after 3 years	ASTM C1549 (uncleaned)	0.70	0.43	0.64
CRRC – Initial thermal emittance	ASTM C1371	0.90	0.89	0.86
CRRC – Initial thermal emittance after 3 years	ASTM C1371 (uncleaned)	0.86	0.88	0.87
LEED – Thermal emittance	C1371	0.90	0.89	0.86
Solar Reflectance Index (SRI)	ASTM E1980	99	53	86
Solar Reflectance Index (SRI) – aged 3 years	ASTM E 1980	85	48	77

EXTREME Testing for Severe Climates

ASTM Standard D6878 is the material specification for Thermoplastic Polyolefin-Based Sheet Roofing. It covers material property requirements for TPO roof sheeting and includes initial and aged properties after heat and xenon-arc exposure. As stated in the scope of the standard, “the tests and property limits used to characterize the sheet are values intended to ensure minimum quality for the intended purpose.” Versico’s goal is to produce TPO that delivers maximum performance for the intended purpose of roofing membranes. Maximum performance requires the membrane to far exceed the requirements of ASTM D6878.

Heat Aging accelerates the oxidation rate that roughly doubles for each 18°F (10°C) increase in roof membrane temperature. Oxidation (reaction with oxygen) is one of the primary chemical degradation mechanisms of roofing materials.

Q-Trac testing combines accelerated weathering with real-world conditions using an array of ten mirrors to reflect and concentrate full spectrum sunlight onto membrane test specimens. The Q-Trac device automatically tracks the sun’s path from morning to night. Also, it adjusts to compensate for seasonal changes in the sun’s altitude. Eight years in Q-Trac testing is equal to 40 years of real-world exposure. Versico requires its VersiWeld TPO membranes to pass the equivalent of 40 years of exposure in the Q-Trac.

VERSICO EXTREME TESTING – HEAT AGING

	ASTM Requirement		VersiFleece TPO Results
ASTM Test	240°F	32 weeks*	>128 weeks
*Comparable to 3,120 weeks (60 years) at 185°F for 8 hrs/day.			

Heat Aging accelerates the oxidation rate that roughly doubles for each 10°C (18°F) increase in roof membrane temperature. Oxidation (reaction with oxygen) is one of the primary chemical degradation mechanisms of roofing materials.

VERSICO EXTREME TESTING – ENVIRONMENTAL CYCLING

– 10 days heat aging at 240°F (116°C) followed by 5 days water immersion at 158°F (70°C)
Followed by 5,040 kJ/m ² (2,000 hrs. at 0.70 W/m ² irradiance) xenon-arc exposure

Environmental Cycling subjects the membrane to repeated cycles of heat aging, hot-water immersion or acid fog followed by xenon-arc exposure.

VERSICO TESTING – Q-TRAC

	ASTM D6878 Requirement	VersiWeld Requirement
ASTM TEST N/A	N/A	Equivalent of 40 years of exposure

RADIATIVE PROPERTIES (INITIAL) FOR SPECIAL COLORS

	Reflectance	Emittance	SRI
Medium Bronze	0.28	0.86	29
Rock Brown	0.25	0.87	26
Slate Gray	0.38	0.87	42
Terra Cotta	0.25	0.86	25
Patina Green	0.25	0.88	25

Solar Reflectance Index (SRI) is calculated per ASTM E1980. The SRI is a measure of the roof’s ability to reject solar heat, as shown by a small temperature rise. It is defined so that a standard black (reflectance 0.05, emittance 0.90) is 0 and a standard white (reflectance 0.80, emittance 0.90) is 100. Materials with the highest SRI values are the coolest choices for roofing. Due to the way SRI is defined, particularly hot materials can even take slightly negative values and particularly cool materials can even exceed 100.

*ENERGY STAR recommends that using the Roof Savings Calculator (rsc.ornl.gov), which factors in both heating and cooling costs, to determine whether a cool roof will be an energy efficient choice for your geographic climate and building type.

VERSIFLEECE TPO MEMBRANES

Physical Property	Test Method	SPEC. (Pass)	VersiFleece TPO
Tolerance on Nominal Thickness, %	ASTM D751	+/-10	+/-10
Thickness over Fleece, min			
100-mil (2.54 mm)			.045 (1.14)
115-mil (2.92 mm)			.060 (1.52)
135-mil (3.43 mm)			.080 (2.03)
Weight, lbm/ft ²			
100-mil	—	—	0.27
115-mil	—	—	0.33
135-mil	—	—	0.46
Breaking Strength, min, lbf (kN)	ASTM D751 Grab Method	220 (1)	350 (1.6) 450 (2) 500 (2.2)
100-mil			
115-mil			
135-mil			
Elongation at break of internal fabric, %	ASTM D751	15	25
Tearing Strength, min, lbf (N)	ASTM D751 B Tongue Tear	55 (245)	100 (445)
100- & 115-mil, 135-mil			
Puncture Resistance, Joules	ASTM D5635		
100-mil		—	17.5
115-mil		—	25
135-mil		—	30.0
Puncture Resistance, lbf	FTM 101C Method 2031	350	450
100-mil			
115-mil		400	500
135-mil		425	525
Brittleness point, max, °F (°C)	ASTM D2137	-40 (-40)	-50 (-46)
Linear Dimensional Change, %	ASTM D1204	± 1 max	-0.2 typical
Field Seam Strength, lbf/in. (kN/m)	ASTM D1876		
ASTM D1876 tested in peel			
100-mil		25 (4.4)	50 (8.8)
115-mil		25 (4.4)	60 (10.5)
135-mil		40 (7.0)	70 (12.3)
Water Vapor Permeance, Perms	ASTM E96 Proc B	—	0.10 max 0.05 typical
Resistance to Microbial Surface Growth, Rating (1 is very poor, 10 is no growth)	ASTM D3274	—	9–10 typical
Properties after heat aging –ASTM D573, 670 hrs. at 240°F	ASTM D573		
Breaking strength, % retained		—	90 min.
Elongation reinf. % retained		—	90 min.
Tearing Strength, % retained		—	60 min.
Weight Change, %		—	± 1.0 max
Ozone Resistance 100 pphm, 168 hours	ASTM D1149	No cracks	No cracks
Resistance to Water Absorption After 7 days immersion @ 158°F (70°C) Change in mass, max, % (one side)	ASTM D471	±3.0	0.90
Resistance to Outdoor (Ultraviolet) Weathering Xenon-Arc, total radiant exposure at 0.70 W/m ² irradiance, 80°C black panel temp.	ASTM G155	No cracks No loss of breaking or tearing strength	No cracks No loss of breaking or tearing strength
100-mil			17,640 kJ/m ²
115-mil			20,160 kJ/m ²
135-mil			27,720 kJ/m ²

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.